TECHNICAL DATA SHEET



Product name:

FIBRAN filter SF32

Material: PI

Application: Geotextile for inverted roofs

PROPERTY	METHOD	UNITS	NOMINAL VALUE	MINIMUM	MAXIMUM	
	FUN	CTIONALITY: HYDR.	AULIC PROPERTIES			
Opening size (O ₉₀)	EN ISO 12956	Mm	140	-	-	
Permeability (V _{iH50})	EN ISO 11058	10 ⁻³ .m/s	70	-	-	
Permeability at 20 kN/m²	DIN 60500-4	10 ⁻⁴ .m/s	4,6	-	-	
Permeability at 200 kN/m²	DIN 60500-4	10 ⁻⁴ .m/s	2,9	-	-	
Flow rate at 10 cm WH	BS 6906-3	Im ⁻² /s	110	-	-	
	PH	IYSICAL AND MECH	ANICAL PROPERTIES			
Mass per unit area	EN ISO 9864	g/m²	110	-	-	
Thickness under 2 kN/m ²	EN ISO 9863-1	mm	0,43	-	-	
Thickness under 200 kN/m ²	EN ISO 9863-1	mm	0,35	-	-	
Energy absorption	EN ISO 10319	kJ/m²	3,0	-	-	
Tensile strength	EN ISO 10319	kN/m	7,0	-	-	
Elongation	EN ISO 10319	%	45	_	_	
Tensile strength at 5%	EN ISO 10319	kN/m	3,3	_	_	
Puncture CBR	EN ISO 12236	N	1.000	_	_	
Dynamic Cone Puncture	EN ISO 13433	mm	35	_	_	
Grab strength			625		_	
	ASTM D 4632	N				
Tear strength	ASTM D 4533	N	290	-	-	
		DURAI	BILITY			
Predicted to be durable for a minimum	<u> </u>					
Natural UV light	Good resistance up to several months in direct sunlight. Nevertheless, prolonged exposure particularly in tropical sunlight can cause strength losses. Product should be covered after 2 weeks of installation.					
Moisture	Does not absorb moisture					
Rot, Mildew	Unaffected	Unaffected				
Natural occurring acids and alkali	Unaffected					
Oxydation resistance	EN ISO 13438	100% retained strength				
Chemical resistance	EN 14030	100% retained strength				
Microbiological Resistance	EN 12225	EN 12225 100% retained strength				
		ADDITIONAL	PROPERTIES			
Length		mm	50.000	-	-	
Width		mm	2.100	-	-	
Area		m ²	105	-	-	
Roll diameter		mm		-	-	
Roll weight		kg	11,6	-	-	
Polymer	100% polypropylene					
Melting point	165 °C					
Colour		Grey				

Issuing date: 01/06/2017

Copyright © 2017 FIBRAN S.A. 56010, Thessaloniki, Greece. All rights reserved. FIBRAN filter is a registered trademarks or trademarks



Some test methods are modified according to the EN 13859-2:2014 and/or according to the FIBRAN ISO 9001:2008 certified quality system (for details please contact your regional FIBRAN representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revisions a new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, FIBRAN makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specifiedherein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature